

## High-Build Anti-Corrosive Primer Surfacer

### PRODUCT DESCRIPTION AND USES:

A two pack urethane primer-surfacer suitable for use in conjunction with other primers and topcoats to produce smooth high quality finishes on a variety of substrates. Has excellent sanding properties and is fast drying

### PHYSICAL PROPERTIES:

Colour:	White & Grey	
Gloss Level:	Flat	
Volume Solids:	48%	
Product Density:	1.48Kg/litre	
Mixing Ratio:	4 parts by volume part A V-62 to 1 part by volume Z-62 hardener Mix well and allow to stand 15 mins before use	
Pot Life:	6 hours @ 25°C	
Drying Time:	Touch dry 1 hours	Hard dry 2 hours @ 25°C
	Recoat 4 hours (min)	Recoat 48 hours (max)

**Note:** Drying times and Pot life are increased at lower temperatures.

### APPLICATION DATA:

Suitable for application by airless or pressure spray, brush or roller.

Airless Spray:	Use 28.1 pump and 0.3 mm fluid orifice.
Pressure Spray:	Add approx 10% T-51 thinner and spray at 400 Kpa atomizing pressure, 100-200 Kpa pot pressure.
Recommended Dry Film Thickness:	125um
Theoretical Spreading Rate:	4 sq.m/litre
Thinning:	Not required for brush or roller application. For pressure spray application up to 20% of T-26 Thinner may be added
Equipment Cleaning:	Clean all equipment immediately after with T-26 Thinner

### **SURFACE PREPARATION:**

Surfaces should be free from grease, salt and should be dry. Remove loose rust, scale and foreign surface matter.

The performance and service life of a protective coating system is dependent upon a number of criteria. These criteria include factors such as choice of coating system, ambient conditions under which the system is to be applied and the standard of surface preparation to be undertaken prior to application of the paint. Of these considerations, the most important factor is in establishing and maintaining a high standard of surface preparation. Failure to ensure high standards of surface preparation will inevitably have a detrimental effect on the eventual life and performance of the coating system applied.

**For specific standards and recommendations contact Seahorse Marine Paints.**

### **STORAGE AND PACKING:**

**Storage:** The Product must be stored in accordance with national regulations. Preferred storage conditions are to keep the containers in a dry space provided with adequate ventilation. The containers should be sealed tightly.

**Packing content:** 1 Litre, 4 Litre 20 Litre. Pack size includes part A and B.

### **HEALTH AND SAFETY:**

Please observe the precautionary notices displayed on the containers. Spray under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on skin should be removed with suitable cleaner, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

**For detailed information on the health and safety hazards and precautions for use of this product, please refer to the Material Safety Data Sheet.**

**DISCLAIMER:** *The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data with out notice.*

ISSUED SEPTEMBER 2009.  
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED.



Pyramid Paints - Seahorse Marine Paints - 26/B Coburg Road Alberton South Australia 5014  
Phone (08) 83411337 - Fax (08) 3411385