

Eco-Fast Marine Fouling Release Coating

PRODUCT DESCRIPTION AND USES:

ECO-FAST is a two-pack Modified Polyurethane Coating with excellent gloss retention and resistance to weathering providing a very durable coating on most substrates. The coating has very excellent resistance to abrasion, chemicals, solvents and ultraviolet degradation. It dries rapidly and can be re-coated with suitable surface preparation.

Developed for the use on regularly used Marine Craft, releasing on toxins into the marine environment. Marine organisms are easily removed

Due to a 60% reduction in friction ECO-FAST gives a 9% to 10% reduction in fuel usage. Since lower RPMs are needed to maintain speed, engine wear is reduced. For sailboats, the reduced drag produces higher speeds in a given wind strength.

PHYSICAL PROPERTIES:

Colour:	Wide range available inc AS 2700
Gloss Level:	Gloss
Volume Solids:	52 %
Product Density:	1.18 Kg / litre White (other colours may vary)
Mixing Ratio:	4 parts by volume part A X-70 to 1 part by volume Z-53 hardener Mix well and allow to stand 20 mins before use
Pot Life:	6 hours @ 25 °C
Drying Time:	Touch dry 2 hours. Hard dry 8 hours. Re-coat 6 hours

APPLICATION DATA:

Suitable for application by airless or conventional spray, brush or roller.

Airless Spray:	Use 28:1 pump and 0.3 mm fluid nozzle
Conventional Spray:	Use approximately 400 KPa atomising air pressure and apply in two wet coats with 15-min flash off between coats.
Recommended total dry Film Thickness:	80um
Theoretical Spreading Rate:	6 sq.m/litre (apply in 2 coats)
Thinning:	Normally not required for brush or roller application. For spray application, up to 20% of T-26 Thinner may be added
Equipment Cleaning:	Clean all equipment immediately after with T-26 Thinner

SURFACE PREPARATION:

Surfaces should be free from grease, salt and should be dry. Apply over suitably primed surfaces, which are clean, dry and free from oil, grease and any other contaminants.

The performance and service life of a protective coating system is dependent upon a number of criteria. These criteria include factors such as choice of coating system, ambient conditions under which the system is to be applied and the standard of surface preparation to be undertaken prior to application of the paint. Of these considerations, the most important factor is in establishing and maintaining a high standard of surface preparation. Failure to ensure high standards of surface preparation will inevitably have a detrimental effect on the eventual life and performance of the coating system applied.

For specific standards and recommendations contact Seahorse Marine Paints.

STORAGE AND PACKING:

Storage: The Product must be stored in accordance with national regulations. Preferred storage conditions are to keep the containers in a dry space provided with adequate ventilation. The containers should be sealed tightly.

Packing content: 1 Litre, 4 Litre 20 Litre. Pack size includes part A and B

HEALTH AND SAFETY:

Please observe the precautionary notices displayed on the containers. Spray under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on skin should be removed with suitable cleaner, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, please refer to the Material Safety Data Sheet.

DISCLAIMER: *The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data with out notice.*

ISSUED SEPTEMBER 2009.
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED.



Pyramid Paints - Seahorse Marine Paints - 26/B Coburg Road Alberton South Australia 5014
Phone (08) 83411337 - Fax (08) 3411385